



€

Ecolabe

## CARCELOR DE LA CARDEL A CENTRE A CENTRE

OROPRO TOTAL is a washable, matte water-based paint with maximum coverage. Formulated with acrylic copolymers, it is suitable for interior and exterior decoration with a high-quality finish. It contains biocides, which provide the paint with fungicidal and anti-mold protection. The product is breathable and offers excellent whiteness.

| Physical parameters              |   |
|----------------------------------|---|
| Viscosity (Brookfield sp6 10rpm) | 20000 – 28000 cpoise  |
| Specific gravity                 | 1,57-1.60 g/mL  |
| Sólids content                   | 63%   |
| VOC                              | <10 g/LThe limit value(2010) Directive 2004/42/EC for this product (sub. cat. A/a): 30g/L |
| Colour                           | White and colours   |
| Spreading rate                   | 8-11 m <sup>2</sup> /L (150 – 200 g/m <sup>2</sup> )                                      |
| In-can appearance                | Viscous liquid  |
| Dry film appearance              | Matte, covering and washable finish   |
| Fire classification              | B-s1,d0   |
| Stability (unopened container)   | 12 months at 10 – 25°C  |
| Gloss 60°                        | <3%   |
| Washability                      | Class 2 (UNE 13.300)  |

| Product use information |  |  |  |  |  |  |  |
|-------------------------|--|--|--|--|--|--|--|
| Surface                 | Cement, concrete, plaster (do not apply over glue, distemper or lime)  |  |  |  |  |  |  |
| Surface preparation     | The surface must be dry, well-cured, without stains, saltpetre, sand, or cracks. According to NTE-RPP-24.                                  |  |  |  |  |  |  |
| Product preparation     | Do not paint below 7°C or during rainy weather. Thoroughly homogenize the product before use.  |  |  |  |  |  |  |
| Application method      | Brush, Roller, Pneumatic Spray Gun   |  |  |  |  |  |  |
| Dilution                | Up to 10-20% with water (for the first coat)   |  |  |  |  |  |  |
| Aplicatión              | 1 first coat diluted with a10-20% of water to aloud a good penetration, and 2 more finishing coats undiluted at 40 - 50 µm.                |  |  |  |  |  |  |
| Drying                  | Touch dry: 30 minutes Drying time is greatly influenced by the grammage, type and condition of the substrate and environmental conditions. |  |  |  |  |  |  |
| Overcoat                | 4 – 6 hours  |  |  |  |  |  |  |
| Cleaning                | WATER  |  |  |  |  |  |  |

| Application process | Primer     | Top Coat   |
|---------------------|------------|------------|
| Plaster, Concrete   | OROPRO 074 | OROPRO 074 |

| Additional information |   |
|------------------------|---|
| Safety                 | Check the labeling on the container. For more information, request the Safety Data Sheet. |
| Storage time           | l year  |

Instructions included in this technical data sheet and its advices have been got from our own experiences and they should be taken as guidelines, with no commitment from us. Values shown in this technical data sheet are only a reference and must not be considered as strict. The customer can and should check the goods provided by us, verifying they are right and valid for their offered purposes. It is completely out of our control the correct application of the product as well as its adequate use, variable working circumstances, etc, so this means the customer is responsible for them. This stated, we completely guarantee the quality of our products, as a consequence of our sales and delivery commitments previously established.

| Producto         | Código artículo. | Marca  | Autor         | Fecha    | Versión | Reemplaza            | Página | Idioma |
|------------------|------------------|--------|---------------|----------|---------|----------------------|--------|--------|
| OROPRO TOTAL 074 | 00R074XXXZZZ     | OROPAL | IRURENA GROUP | 04.07.25 | 1       | Any previous version | 1/1    | EN     |