



OROPALGUM 115F

DRIP-FREE FIBRE-REINFORCED COATING

Waterproof membrane based on styrene acrylic emulsion, reinforced with fiberglass that enhances its resistance to expansion and contraction movements, minimizing crack formation on the applied surface. Suitable for waterproofing roofs, easy to apply, providing a continuous thick layer coating that allows for repairing areas prone to cracks or with tendencies to form them. Withstands exterior aging and maintains elasticity below 0°C. Can be occasionally walked on or used, with resistance to staining. Contains preservatives providing fungicidal and anti-mold protection to the paint.

Physical Parameters

Viscosity (Brookfield sp6 10rpm)	23000 – 43000 cP
Specific weight	1.35 – 1.39 g/mL
Solids	58 – 60 %
VOC	< 30 g/L Limit value (2010) according to directive 2004/42/EC for this product (sub. cat. A/c): 40 g/L
Colour	White, English Red, Tile, Green, Grey, and Black
Coverage	1 m ² /L (1400 g/m ²) (per coat)
Appearance in container	Viscous liquid
Dry film appearance	Elastic matt finish with good levelling
Stability (unopened container)	12 months at 10 – 25°C
Gloss	< 5 %
Adhesion	100 % (Max: GT0)

Product Use

Substrate	Cement, concrete, stone, and brick
Substrate Preparation	The surface should be dry, free from efflorescence, stains, or cracks wider than 0.8 mm. Advisable to seal
Product Preparation	Do not paint at temperatures below 10°C, or in rainy, misty, or frosty conditions. Before applying, thoroughly mix the product with a spatula
Application System	Brush and Roller
Dilution	Up to 15% with water (for the first coat).
Application	Seal the surface with OROIMPER 106 or with a coat of OROIMPER 115F diluted at 15% with water. Apply two coats of OROIMPER 115F, 500 µm dry each, allowing each coat to dry thoroughly.
Drying/Curing	Touch dry: 4 – 12 hours (depending on humidity)
Drying time is greatly influenced by weight, type and condition of the substrate, and environmental conditions.	
Recoating	18 – 24 hours (depending on humidity)
Cleaning	WATER

Recommended System

	Primer	Finish
Terraces	OROIMPER 115F (diluted) OROIMPER 106	OROIMPER 115F

Additional information

Safety	Check container labelling. For further information, ask for the Material Safety Data Sheet
Storage	1 year

Instructions included in this technical data sheet and its advices have been got from our own experiences and they should be taken as guidelines, with no commitment from us. Values shown in this technical data sheet are only a reference and must not be considered as strict. The customer can and should check the goods provided by us, verifying they are right and valid for their offered purposes. It is completely out of our control the correct application of the product as well as its adequate use, variable working circumstances, etc, so this means the customer is responsible for them. This stated, we completely guarantee the quality of our products, as a consequence of our sales and delivery commitments previously established.

Product	Product code	Brand	Author	Date	Version	Replaces	Page	Language
OROIMPER 115F	01R115XXXZZFI	OROPAL	IRURENA GROUP	05.01.24	1	Any previous version	1/2	EN