

# OROKRIL 161

## PAINT FOR FACADES

Silky matte plastic paint, highly washable and resistant to rubbing. Excellent for interior and exterior decoration due to its good resistance to water and ultraviolet rays. It contains biocides that provide the paint with fungicide and anti-mold protection. Its properties include its excellent whiteness and coverage.

### Physical features

Viscosity (Brookfield $sp_6$ 10rpm)	15000 – 25000 cpoise	
Specific weight	1,45 g/mL	
Solids	60%	
VOC	<40 g/L	Limit value (2010) according to directive 2004/42 / EC for this product (sub-cat.A / c): 40 g / L
Color	White	
Efficiency	7 – 9 m <sup>2</sup> /L	(170 – 200 g/m <sup>2</sup> )
Appearance in the can	Viscous liquid	
Appearance in dry film	Matt silky finish, opaque and highly washable	
Fire classification	B-s1,d0	
Stability (without opening the can)	12 months at 10 – 25°C	
Gloss	2 – 5%	
Washability	>10000 doble passes	

### Product use

Support	Cement, concrete, plaster, stone, brick ...
Support preparation	The surface must be dry, well set, without salt, mold, debris, sands or fissures. According to NTE-RPP-24.
Product preparation	Do not paint below 7°C, nor with rainy weather. Homogenize the product well before use.
Application system	Brush, Roller, Pneumatic gun, Airless gun
Dilution	Up to 20% water (the first hand)
Application	Seal with a first coat of OROIMPER 106, or a coat of OROKRIL 161 diluted to 20% with water to penetrate well, and 2 more coats of undiluted finish at 50 - 60 µm dry film thickness.
Drying/curing	Dry touch: 30 minutes Drying time is very influenced by the applied quantity, the environment and the substrate's type and condition.
Repaint	4 – 12 hours
Cleaninig	WATER

Instructions included in this technical data sheet and its advices have been got from our own experiences and they should be taken as guidelines, with no commitment from us. Values shown in this technical data sheet are only a reference and must not be considered as strict. The customer can and should check the goods provided by us, verifying they are right and valid for their offered purposes. It is completely out of our control the correct application of the product as well as its adequate use, variable working circumstances, etc, so this means the customer is responsible for them. This stated, we completely guarantee the quality of our products, as a consequence of our sales and delivery commitments previously established.

Product	Product code	Brand	Author	Date	Version	Replaces	Page	Language
OROKRIL 161	01R161XXXZZ	OROPAL	IRURENA GROUP	03.01.24	1	Any previous version	1/2	EN

Recommended system	Primer	Topcoat
Plaster, concrete	OROIMPER 106 OROKRIL 161	OROKRIL 161

Additional information	
Security	Consult package labeling. For more information request the Safety Sheet.
Storage time	1 year

Instructions included in this technical data sheet and its advices have been got from our own experiences and they should be taken as guidelines, with no commitment from us. Values shown in this technical data sheet are only a reference and must not be considered as strict. The customer can and should check the goods provided by us, verifying they are right and valid for their offered purposes. It is completely out of our control the correct application of the product as well as its adequate use, variable working circumstances, etc, so this means the customer is responsible for them. This stated, we completely guarantee the quality of our products, as a consequence of our sales and delivery commitments previously established.

Product	Product code	Brand	Author	Date	Version	Replaces	Page	Language
OROKRIL 161	01R161XXXZZ	OROPAL	IRURENA GROUP	03.01.24	1	Any previous version	2/2	EN