

OROLEX 260

ALKYD ENAMEL

Soft touch matt alkyd enamel. with anticorrosive effect. Features good leveling and excellent brushability. Recommended as a topcoat for interior and exterior doors, windows, baseboards, frames, wardrobe etc....

Physical parameters

Viscosity (Ford cup #4)	120-240"	(depending on the colour)
Specific gravity	1.35-1.50 g/cc	(depending on the colour)
Sólids content	73-78%	(depending on the colour)
VOC	<500 g/L	Directive 2004/42/CE: Limit value (2010) for this product (sub. cat. A/i): 500 g/L
Colour	White, Black	
Spreading rate	14-19 m ² /L	(70 – 100 g/m ²)
In-can appearance	Viscous liquid	
Dry film appearance	High covering and leveling matt enamel	
Stability	12 months at 10 – 25°C	
Gloss	<4%	
Adhesion	100% (Máx: GT0)	

Product use information

Surface	All types of properly primed surfaces
Surface preparation	Surfaces to be painted must be clean and dry. According to NTE-RPP-34-35
Product preparation	Stir thoroughly the content of the container before use.
Application method	Brush, Roller, Pneumatic spray, Airless spray
Dilution	Brush/roller application: Do not dilute or max. 3% with ORODIS 719 Spray application: Up to 15% with ORODIS 717
Application	Apply 1 – 2 coats of 30 – 40 µm dry film thickness
Drying	Touch drying time: 4 – 6 hours Drying time is very influenced by the dry film weight, type and state of the substrate and weather conditions.
Recoatable	24 hours
Cleaning	ORODIS 719 or White spirit

Application process

	Primer	Intermediate	Top coat
Iron, steel	OROPRIMER 420		OROLEX 260
Wood	OROPRIMER 401		OROLEX 260

Additional information

Safety	Consult package labelling. For further information, ask for the Material Safety Data Sheet
Storage	1 year

Instructions included in this technical data sheet and its advices have been got from our own experiences and they should be taken as guidelines, with no commitment from us. Values shown in this technical data sheet are only a reference and must not be considered as strict. The customer can and should check the goods provided by us, verifying they are right and valid for their offered purposes. It is completely out of our control the correct application of the product as well as its adequate use, variable working circumstances, etc, so this means the customer is responsible for them. This stated, we completely guarantee the quality of our products, as a consequence of our sales and delivery commitments previously established.

Product	Product code	Brand	Author	Date	Version	Replaces	Page	Language
OROLEX 260	02R284XXXZZZ	OROPAL	IRURENA GROUP	03.01.24	1	Any previous version	1/1	EN