

# OROSPORT 332

## PAINTING OF FINISH FOR VELODROMES

Non-slip finish based on special resins for painting velodrome surfaces. Coarse-grained paint for the painting of slopes with slopes between 25° and 45°. In general, this type of paint covers 20 - 25% of the total surface of the velodrome.

### Physical parameters

Viscosity (Brookfield sp6 10rpm)	10000 – 20000 cpoise
Specific gravity	1,00 – 1,35 g/mL depending the colour
Sólids content	65 - 70% depending the colour
Colour	UCI 1, 3, 4, 6, 7, 8
Spreading rate	6 – 7 m <sup>2</sup> /Kg (130 – 150 g/m <sup>2</sup> )
In-can appearance	Viscous liquid
Dry film appearance	Matte film with fine-grade rough finish
Stability	12 months at 10 – 25°C
Gloss	2,5 – 4,5%
Adhesion	100% (Máx: GT0)
Anti-slip grade	G-2 straights

### Product use information

Surface	Cement, concrete
Surface preparation	The surface must be primed and completely dry.
Product preparation	Before applying, homogenize the product well with a spatula
Application method	Roller
Thinning	It does not diluted
Aplicación	Apply at least 2 coats of OROSPORT 332 undiluted, so that the finish has a good consistency
Drying	Touch drying time: 3 - 5 hours Drying time is very influenced by the dry film weight, type and state of the substrate and weather conditions...
Overcoat	24 hours
Cleaning	ORODIS 719

Recommended system	Impregnation	Primer	Topcoat
Concrete, Cement	OROSPORT 325	OROSPORT 325	OROSPORT 332

### Additional information

Safety	Consult package labelling. For further information, ask for the Material Safety Data Sheet
Storage	1 year

Instructions included in this technical data sheet and its advices have been got from our own experiences and they should be taken as guidelines, with no commitment from us. Values shown in this technical data sheet are only a reference and must not be considered as strict. The customer can and should check the goods provided by us, verifying they are right and valid for their offered purposes. It is completely out of our control the correct application of the product as well as its adequate use, variable working circumstances, etc, so this means the customer is responsible for them. This stated, we completely guarantee the quality of our products, as a consequence of our sales and delivery commitments previously established.

Product	Product code	Brand	Author	Date	Version	Replaces	Page	Language
OROSPORT 332	03R332XXXZZ	OROPAL	IRURENA GROUP	16.10.18	1	Any previous version	1/1	EN